

WALSC AAC ADHESIVE

Technical Data



APPLICATION

1. Apply Walsc AAC Adhesive to the horizontal and vertical surfaces of the AAC panels or blocks that will be adhered.
2. The applied thickness of Walsc AAC Adhesive should be approximately 2-3mm.
3. Position the AAC panels or blocks by gently tapping with a rubber mallet and use a spirit level to check for alignment.
4. The mixed material is usable for up to 2 hours at 23°C and 50% relative humidity.

DRYING TIME

Walsc AAC Adhesive will cure after 24 hours at 23°C. Application in conditions below 10°C will extend the drying time whilst application in conditions above 35°C will shorten the drying time and premature curing of the adhesive could result in the adhesive not reaching a full bond.

Walsc AAC Adhesive should not be applied in rain or frost or when rain is imminent.

COVERAGE

Coverage will vary depending on the condition of the surface and site conditions. As a guide, 20kg of Walsc AAC Adhesive will be sufficient for approximately 20/25m² of 75/50mm AAC panel area.

CLEAN UP

Clean all tools in water immediately after use.

SHELF LIFE

12 months from date of manufacture, when stored in a dry place, in original unopened packaging.

SUBSTRATE CONDITIONS

Must be applied over properly prepared substrates that are free of dirt, dust, grime and any other contaminants.

MIXING

1. Add approximately 5-5.5L of clean water to a bucket and gradually add 20kg of Walsc AAC Adhesive while stirring slowly.
2. Allow the mix to stand for 3-5 minutes before use.
3. Do not remix if Walsc AAC Adhesive starts to harden in the pot.



DISCLAIMER

Sipo Building Solutions Pty Ltd will not accept responsibility for any misuse of this product or if not applied by a skilled and experienced applicator and in accordance with our technical specifications. Due to our policy of continuing product improvement, Sipo Building Solutions Pty Ltd reserves the right to change these specifications without further notice. Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and compensation for any other reasonably foreseeable loss or damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure.

HEALTH AND SAFETY

Product Contains

Non-hazardous components, 40-70%
Portland Cement, 65997-15-1, 30-60%



Classification of Product

Skin Irritation. 2. H315
Eye Irritation. 2A H319
STOT SE. 3. H335
STOT RE. 2 H373

Hazard Statements

H373 May cause damage to organs through prolonged or repeated exposure
H319 Causes serious eye irritation
H335 May cause respiratory irritation
H315 Causes skin irritation

Precautionary Statements

P304+P340 IF INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing
P332+P313 If skin irritation occurs: Get medical advice/attention
P501 Dispose of contents/container in accordance with local regulations
P305+P351+P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do so. Continue rinsing
P312 Call a POISON CENTER or doctor/physician if you feel unwell
P260 Do not breathe dust/fume/gas/mist/vapours/ spray
P280 Wear protective gloves, eye and face protection

Please refer to the MSDS for additional information, available at www.walsc.com.au

